а





С



Element	Concentration, wt. %		
	Spectrum 1	Spectrum 2	Spectrum 3
Al	8.88	9.94	3.33
Cr	25.26	13.86	10.91
Fe	Bal.	Bal.	Bal.
Mo	2.46	1.25	_
Y	_	5.45	—
Zr	_	15.5	16.88
0	_	_	26.84

Fig. 3. SEM images of the initial surface of FeCrAl doped with molybdenum + yttrium + zirconium (a, b), detail of the surface after sputtering (c)and the EDS analyses from the points marked in the images (b, c)